Epojet

Precision solutions for crack repair

Strengthen and protect with confidence

The *Epojet* family of epoxy injection resins delivers reliable, high-performance solutions for repairing cracks in structural concrete, masonry and wood. Designed to penetrate deeply and seal effectively, these moisture-tolerant, 100%-solids products provide lasting strength, whether applied by pressure injection, by gravity feed, or when combined with sand for epoxy mortar applications.

MAPEI USA

MAPEI®

	Number of components	Gel time	Yield, neat per mixed bag	Bond strength, 7 days	Bond strength, 14 days	Viscosity	Pot life	Tack-free time at 73°F (23°C)	Minimum temperature	Compressive strength, 7 days	Interior and exterior applications	Residential	Commercial
Epojet	2	30 min.	231 cu. in. (0.0038 m³)	N/A	2,754 psi (19.0 MPa)	410 cps	~ 25 min.	30 min.	40°F (4°C)	12,180 psi (84 MPa)	•	•	•
Epojet LV	2	60 min.	693 cu. in. (0.01 m³)	N/A	2,980 psi (20.6 MPa)	170 cps	~ 25 min.	30 min.	40°F (4°C)	12,720 psi (87.7 MPa)	•	•	•
Epojet SLV	2	80 min.	1,155 cu. in. (0.019 m³)	> 1,000 psi (6.90 MPa)	> 3,000 psi (20.7 MPa)	80 to 100 cps	20 to 25 min.	4 to 6 hrs.	40°F (4°C)	> 10,000 psi (69.0 MPa)	•	•	•

Epojet

High-modulus, low-viscosity, epoxy injection resin for crack repair

Epojet is a high-strength, two-component, 100%-solids, low-viscosity, epoxy resin for pressure injection and sealing of cracks in structural concrete, masonry and wood.

Learn more

Epojet LV

Very low-viscosity, epoxy injection resin for crack repair

Epojet LV is a moisture-tolerant, two-component, 100%-solids, very low-viscosity, epoxy injection resin that deeply penetrates as well as seals dry and damp hairline, non-dynamic cracks. *Epojet LV* may be applied by pressure injection or gravity feed, and can also be combined with sand to become an epoxy mortar.

Learn more

Epojet SLV

Super low-viscosity, epoxy injection resin for crack repair

Epojet SLV is a moisture-tolerant, two-component, 100%-solids, super low-viscosity, epoxy injection resin that penetrates deeply and seals dry and damp hairline, non-dynamic cracks.

Learn more